

Original Article

Effectiveness of Finishing and Polishing on the Surface Roughness of Nanofilled Composite- A Clinical Study

Piyush Gandhi¹, Taranjot Kaur², Inderpreet Singh³, Simerpreet Kaur Bagga⁴

¹Assistant Professor, Department of Oral Pathology, ³Associate Professor, Department of Conservative Dentistry and Endodontics, Dasmesh Institute of Research and Dental Sciences, Faridkot, Punjab, ²Ex-PCMS Dental, Associate Lecturer AFK, ⁴B.D.S.

ABSTRACT:

Background: Dental composite resins have certain properties that will benefit patients according to the patient's cavity. The present study evaluated the effect of various finishing and polishing procedures on the surface roughness of nanofilled composite. **Materials & Methods:** The present study was conducted on 45 recently restored composite teeth. All restorations were divided into 3 groups depending upon finishing and polishing systems. Group I had Shofu finishing and polishing kit, group II had Sof-Lex composite finishing and polishing kit and group III had Mylar Strips. **Results:** The mean value of surface roughness in group I was 0.72, in group II was 0.58 and in group III was 0.36. The difference was significant (P- 0.01). The mean value of surface roughness in group I was 0.78, in group II was 0.66 and in group III was 0.40. The difference was significant (P- 0.01). **Conclusion:** Mylar strip provided the smoothest surfaces followed by Sof-Lex followed by Shofu. The surface texture for the composite improved significantly when sealant is applied after finishing and polishing procedures.

Key words: Composite, Finishing, Polishing.

Received: 18 January 2018

Revised: 16 February 2018

Accepted: 27 February 2018

Corresponding Author: Dr. Piyush Gandhi, Assistant Professor, Department of Oral Pathology, Dasmesh Institute of Research and Dental Sciences, Faridkot, Punjab, India

This article may be cited as: Gandhi P, Kaur T, Singh I, Bagga SK. Effectiveness of Finishing and Polishing on the Surface Roughness of Nanofilled Composite- A Clinical Study. J Adv Med Dent Scie Res 2018;6(4):77-79.

INTRODUCTION

The longevity and the aesthetic appearance of composite restorations greatly depend on the quality of finishing and polishing techniques. Introduction of composite restorative materials in the 1960s marked the beginning of modern cosmetic dentistry by combining the principles of esthetics and tooth conservation. Smooth, highly polished restorations are more esthetically appealing and less susceptible to plaque accumulation and extrinsic discoloration and they also exhibit improved mechanical properties.¹

Dental composite resins have certain properties that will benefit patients according to the patient's cavity. It has a micro-mechanic property that makes composite more effective for filling small cavities where amalgam fillings are not as effective and could therefore fall out. Synthetic resins evolved as restorative materials since they were insoluble, of good tooth-like appearance, insensitive to dehydration, easy to manipulate and reasonably

inexpensive. Composite resins are most commonly composed of Bis-GMA and other dimethacrylate monomers, a filler material such as silica and in most current applications, a photoinitiator.²

Carbide and diamond finishing burs, abrasive impregnated rigid points, impregnated rubber cups and points, aluminium oxide coated abrasive discs, abrasive strips, and polishing pastes are commonly used for finishing and polishing tooth-colored restorative materials. Each of these instruments or devices remove the oxygen inhibited layer of resin but leave the surface of restorative materials with varying degrees of surface roughness. Thus it is important to understand which type of surface-finishing treatments would significantly affect the surface irregularities of different composite resin restorations.³ The present study evaluated the effect of various finishing and polishing procedures on the surface roughness of nanofilled composite.

MATERIALS & METHODS

The present study was conducted in the department of Endodontics. It included 60 recently restored composite teeth. All patients were informed regarding the study and written consent was obtained.

General information such as name, age, gender etc. was recorded. All restorations were divided into 3 groups depending upon finishing and polishing systems. Group I

had Shofu finishing and polishing kit, group II had Sof-Lex composite finishing and polishing kit and group III had Mylar Strips. Then surface sealant (prime & bond) was applied to all treated specimens and the average roughness (Ra) was measured. Results were tabulated and subjected to statistical analysis. P value less than 0.05 was considered significant.


RESULTS

Table I Distribution of teeth

Group I	Group II	Group III	P value
Shofu finishing and polishing kit	Sof-Lex composite finishing and polishing kit	Mylar Strips	1
20	20	20	


Table I shows that group I had Shofu finishing and polishing kit, group II had Sof-Lex composite finishing and polishing kit and group III had Mylar Strips. The difference was non-significant (P= 1).

Graph I Comparison of Surface roughness between different groups using Z-350 (before sealant application)



Graph I shows that the mean value of surface roughness in group I was 0.78, in group II was 0.66 and in group III was 0.40. The difference was significant (P= 0.01).

Graph II Comparison of Surface roughness between different groups using Z-350 (after sealant application)



Graph II shows that the mean value of surface roughness in group I was 0.72, in group II was 0.58 and in group III was 0.36. The difference was significant (P= 0.01).

DISCUSSION

Early studies have shown that the smoothest surface of a resin restoration is attained when the resin is polymerized against an appropriate matrix strip. When a matrix is not used, polymerization of outer layer is inhibited, resulting in a surface layer rich in organic binder with stick and soft consistency. In either case, removal of that outermost resin by trimming and finishing procedures would lead to producing a harder, more wear resistant, and, hence, a more aesthetically stable surface.⁴

The primary goal of finishing is to obtain a restoration with good contour, occlusion, healthy embrasure forms and a smooth surface. Tight margins of the restorations should blend aesthetically into the tooth's natural contours. The resin matrix and the filler particles of composite resins do not abrade to the same degree due to different hardness.⁵

We found that the mean value of surface roughness in group I was 0.78, in group II was 0.66 and in group III was 0.40. The mean value of surface roughness in group I was 0.72, in group II was 0.58 and in group III was 0.36. A study by Bottu et al⁶ used 30 composite discs of dimension 6mm x 3 mm using a custom made stainless steel mould and then randomly divided into 3 subgroups for finishing and polishing by three different methods. Statistically significant difference was observed in surface roughness values before and after sealant application when finished and polished with shofu system. The lowest roughness values, before and after sealant application, was obtained when cured under a Mylar strip and the highest values were obtained when treated with Shofu.

For instance, craters are often formed around hard quartz particles of conventional composite resins after polishing. As consequence, irregularities appear on the surface of the restorations. The filler content of the composite resin also affects roughness, as microfilled composite resins show smoother surfaces than hybrid composite resins. Similarly, the resin matrix composition may also play a role in the final smoothness of the restoration. The finishing and polishing procedure involves some fundamental principles that allow us to better understand its application in dentistry.⁷

In a study by Eslo et al⁸, control group showed the lowest roughness values among the finishing methods, groups 1 and 2 showed significantly higher roughness values than groups 3 and 4 ($P < 0.02$). As for polishing procedures groups 5 and 6 showed significantly higher roughness values than groups 7 and 8 ($P < 0.05$). Multi-step diamond burs and composite points obtained the worst results: they gave high roughness values. Enamel Plus Shiny polishing paste gave very low roughness values, as PoGo polishing discs, which obtained the smoothness surfaces, comparable to that of control group (Mylar strip).

CONCLUSION

Mylar strip provided the smoothest surfaces followed by Sof-Lex followed by Shofu. The surface texture for the composite improved significantly when sealant is applied after finishing and polishing procedures.

REFERENCES

1. Shantanu. The effect of one-step polishing system on the surface roughness of three esthetic resin composite materials. *Oper Dent* 2004; 29(2):203-11.
2. Sarac D, Sarac YS, Kulunk S, Ural C, Kulunk T. The effect of polishing techniques on the surface roughness and color change of composite resins. *J Prosthet Dent* 2006; 96(1):33-40.
3. Jefferies SR. Abrasive finishing and polishing in restorative dentistry: a state-of-the-art review. *Dent Clin North Am* 2007; 51(2):379-97.
4. Ruyter IE. Composites - characterization of composite filling materials: reactor response. *Adv Dent Res* 1988; 2(1):122-9.
5. Neel. The effect of finishing and polishing procedures on the surface roughness of composite resin materials. *J Contemp Dent Pract* 2007; 8(1):27-35.
6. Sarita Singh, Jyoti Mandlik, Kalpana Kanyal, Abhijit Jadhav, Aishwarya Handa. An in-vitro evaluation of effect of three finishing and polishing systems on the surface of nanofilled composite resin. *Indian Journal of Conservative and Endodontics* 2016; 1(2):37-41.
7. Frazier KB, Roeder LB, Debner TL. AL Neme, KB Frazier, LB Roeder, TL Debner. Effect of prophylactic polishing protocols on the surface roughness of esthetic restorative materials. *Oper Dent* 2002; 27(1):50-8.
8. Eslo, Hughes PJ et al. The effect of three finishing systems on four esthetic restorative materials. *Operative Dentistry* 1998; 36-42.

Source of support: Nil

Conflict of interest: None declared

This work is licensed under CC BY: *Creative Commons Attribution 3.0 License*.